

Datasheet revision 1.1

www.chipquik.com

Solder Wire SAC305 Rosin Activated with 2.0% Flux Core 4oz Spool

Product Highlights RA (Rosin Activated) 2.0% Flux Core A stronger activated flux for hard to solder surfaces RoHS 3 and REACH compliant

Sn96.5/Ag3.0/Cu0.5
0.015" (0.38mm)
Rosin Activated
ROM0
217-220°C (423-428°F)
4 oz spool
>60 months

Test Results

Test Requirement	Result
IPC-TM-650: 2.3.32	L: No breakthrough
IPC-TM-650: 2.6.15	M: Slight corrosion
IPC-TM-650: 2.3.28.1	L: <0.05%
IPC-TM-650: 2.6.14.1	L: <1 decade drop (No-clean)
IPC-TM-650: 2.6.3.7	L: ≥100MΩ (No-clean)
IPC-TM-650: 3.4.2.5	Clear and free from precipitation
Electronic Industry Citizenship Coalition (EICC)	Compliant
Articles 33 and 67 of Regulation (EC) No 1907/2006	Contains no substance >0.1% w/w that is listed as a SVHC or restricted for use in solder materials
	IPC-TM-650: 2.3.32 IPC-TM-650: 2.6.15 IPC-TM-650: 2.3.28.1 IPC-TM-650: 2.6.14.1 IPC-TM-650: 2.6.3.7 IPC-TM-650: 3.4.2.5 Electronic Industry Citizenship Coalition (EICC) Articles 33 and 67 of Regulation (EC)

Conforms to the following Industry Standards:J-STD-004B, Amendment 1 (Solder Fluxes):YesJ-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders):YesRoHS 3 Directive (EU) 2015/863:Yes