



Made in the United States of America



### Description

Conductive Drum Liners 2014 do not hold static charge when grounded. The drum liners are constructed from a single layer of carbon loaded polyethylene. The material is non-sloughing, and does not contaminate components it comes in contact with, despite repeated use.

### Specifications

#### Properties

Thickness

Color

Tensile Strength

Elongation

Dart Impact

Tear Strength

Mullen Burst

Puncture

#### Test Method

ASTM D882

ASTM D883

ASTM D1709

ASTM D882

ASTM D774

FED Std 101

#### Value

4.0 mil (0.004", 0.1016 mm)

Black Opaque

MD>2,000 psi

MD 150%

250 to 700 grams @ 26" drop

> 400 lbs/in.

20 - 60 PSI

8 lbs

#### Electrical Properties

Volume Resistivity

Surface Resistivity

#### Test

ASTM D991

ASTM D257

#### Method Value

< 30,000 Ohms/cm

< 30,000 Ohms/sq

#### Heat Sealing

Temperature

Time

Pressure

250 - 375 F

0.5 - 3.5 sec

30 - 70 PSI

#### Chemical Susceptibility

Dilute Acids and Alkalies

Alcohols (Isopropanol)

Ketones (Acetone)

Hydrocarbons (Acetone)

Gasoline

Aromatic Hydrocarbons (Toluene)

#### ASTM D543

Resistant

Resistant

Slight Attack

Moderate Attack

Moderate Attack

Severe Attack

Item	Size	Gallon Size	Quantity
<a href="#">2014 18X24</a>	18" x 24"	5	100 / Box
<a href="#">2014 38X58</a>	38" x 58"	55	50 / Box

Unless specified tolerance is ±10%

Specifications and procedures subject to change without notice.

## VELOSTAT™ CONDUCTIVE DRUM LINER

# PROTEKTIVE PAK

PROTEKTIVE PAK  
13520 MONTE VISTA AVENUE, CHINO, CA 91710  
PHONE (909) 627-2578  
[ProtektivePak.com](http://ProtektivePak.com)

DRAWING  
NUMBER  
2014 18X24

DATE  
February  
2017