

Technical Data Sheet

Product Description

Thermal Insulating Sheet



Material Properties

- High thermal conductivity, low resistance
- Electrical insulation
- High pressure resistance
- High tensile strength

Also Available:

- Cut per drawing and custom shapes
- Optional adhesive

Applications

- ✓ Automotive electronics
- ✓ Adapter
- ✓ Communication equipment
- ✓ Motor Controller
- ✓ High pressure interface
- Semiconductor Optoelectronic Products



EVSC1000FG					
Color		White		Visual	
Composition		Fiber glass		* * *	
Thickness (mm)		0.2~0.5mm		ASTM D751	
Hardness (Shore A)		90		ASTM D2240	
Pressure (Psi)	10	25	50	100	200
(°C*in2/W)	0.59	0.44	0.34	0.29	0.24
Applicable tempure°F/ °C		-50 to 200 °C		* * *	
Electrical					
Dielectric Breakdown Voltage@AC		>4000V		ASTM D149	
Dielectric constant (1MHz)		3.0~3.5		ASTM D150	
Volume resistivity (Ω.cm)		10 ¹¹		ASTM D257	
Fire ro	V0		UL 94		
Thermal conductive					
Thermal conductivity(W/m.k)		3.5		ASTM D5470	
Roł	PASS		IEC 62321		
Halogen		PASS		EN14582	
REACH		PASS		EN14372	

Test fixtures using ASTM D5470. Recorded values include interface thermal resistance. These values are for reference only. The actual application performance is directly related to the applied surface roughness, flatness and pressure.

CR Technology, Inc

💿 55 Chase St. Methuen,

Massachusetts 01844

- 🛛 sales@crtechinc.com
- 978.681.5300

Note: The information provided herein is accurate at time of publication. It is the responsibility of the end-user to confirm compliance to their application. All test data is typical. Therefore, these recommendations and data are for reference only and not as a product warranty.