

Put Ups -

- Perfect for Grounding and Shielding
- 100% Copper Braid
- Provides Excellent Current Transmission

Nominal Size	Part #	Wall Thickness	Min Exp.	Max Exp.	Bulk Spool	Shop Spool	Available Colors	Lbs/ 100′
1/8″	MBC0.13CP	.015″	1/8"	1/4"	250′	25′	Copper	0.90
1/4″	MBC0.25CP	.025″	1/4"	3/8"	100′	25′	Copper	3.00
3/8″	MBC0.38CP	.018″	3/8"	3/4"	100′	25′	Copper	3.10
1/2″	MBC0.50CP	.020″	1/2"	1"	100′	25′	Copper	4.10




## Copper

Glaue	
МВС	

## Bare Copper Braid for a Wide Variety of Applications!

Techflex high purity Copper Sleeve is a 100% copper braid for grounding, shielding, and many other unique projects. Our copper series of metal braids are pure metal with no fillers or coating to provide many years of continuous use. Our braid is suitable for hoses, wires, and other lines on a wide variety of applications. Techflex Bar Copper braid will provide high flexibility and excellent current transmission for your demanding uses. Colors Available: Copper (CP)









Melt Point

ASTM D-2117

1,981°F (1,083°C)

2100°

1800°

1500° 1200°

900° 600°

3009 nº

-300°

-6009



Rating \_\_\_\_\_ Non Flammable



1=No Effect 2=Little Effect 3=Affected

4=More Affected 5=Severely Affected

Aromatic Solvents	1
Aliphatic Solvents	1
Chlorinated Solvents	
Weak Bases	1
Salts	1
Strong Bases	2
Salt Water 0-S-1926	1
Hydraulic Fluid <i>MIL-H-5606</i>	1
Lube Oil <i>MIL-L-7808</i>	1
De-Icing Fluid MIL-A-8243	1
Strong Acids	5
Strong Oxidants	5
Esters/Ketones	1
UV Light	2
Petroleum	2
Fungus ASTM G-21	2
Halogen Free	Yes
RoHS	Yes

## O PHYSICAL PROPERTIES

Monofilament Thickness	.005
ASTM D-204	
Flammability Rating	Non Flammable
Recommended Cutting	Shears
Colors	1
Wall Thickness	.015025

TEMPERATURES

OPERATING

© 2019 Techflex, Inc. - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex, Inc. is strictly forbidden. Techflex product names and logos are registered trademarks of Techflex, Inc., unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's only obligations are those in standard terms of sale for these products and Techflex will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 02-19