



TG-PP-10

Silicone Thermal Putty

REACH Compliant RoHS Compliant

Features

- Thermal Conductivity 10 W/mK
- Single component silicone putty
- Soft and ultra highly compressible for low stress applications
- Suitable to fill gaps from 0.25mm - 8mm

Applications

Consumer Electronics - Set-top boxes, IP routers, ECUs, Memory and Power modules, white goods, telecom infrastructure


Standard Sizes

Pot / Pail
1kg
5kg

Properties

Thermal Conductivity : 10 W/mK

0 0.8 1.2 1.4 1.6 1.7 1.8 2.2 3.2 3.6 4.0 4.5 5.0



Hardness : 50 (Shore 00)

0 5 10 15 20 25 30 40 80



Properties	TG-PP-10	Unit	Test Method
Thermal Conductivity	10	W/mK	ASTM D5470
Viscosity, Brookfield RVT, @ 25° C	Putty	cP	ASTM D792
Colour	White	-	Visual
Mix ratio	1 component		T-Global
Specific Gravity, 25° C	1.2	-	ASTM D792
Hardness	50	Shore 00	ASTM D2240
Operating Temperature Range	-55~+200	° C	T-Global
Evaporation @ 150° C, 24 hours	0.2	%/Wt	ASTM 6814
Shelf Life	12	months	T-Global

Storage

Thermal putty has a shelf-life of twelve (12) months from the date of manufacture, as indicated by the lot number, when stored in the original, unopened container at, or below 25°C.

T-Global Technology (Europe & North America) Limited

Units 1-2 Cosford Business Park, Central Park, Lutterworth, Leicestershire, LE17 4QU, United Kingdom
T +44 (0)1455 553 510 **E** sales@tglobaltechnology.com **W** www.tglobaltechnology.com

Version 5
2021.0222



T-Global Technology are proud to announce the launch of a new company logo and mission statement as part of the ongoing growth and evolution of our company's brand.

NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film does not affect the function of the product. If there is no special requirement, the default depends on T-Global. Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.