

Datasheet revision 1.2

www.chipquik.com

CHIPQUIK® NCSWLF.015.0.202 NCSWLF.015.0.202 Spo6.5/A69.0/cup.5

Solder Wire SAC305 No-Clean with 2.0% Flux Core 0.2oz Tube

Product Highlights No-Clean Synthetic Flux Core The clear, non-corrosive, non-conductive residue is meant to be left on the board. 2.0% flux core Halogen content: None RoHS 3 and REACH compliant

Specifications Alloy: Wire Diameter: Flux Type: Flux Classification: Melting Point: Packaging: Shelf Life:

Sn96.5/Ag3.0/Cu0.5 0.015" (0.38mm) No-Clean Synthetic ROL0 217-220°C (423-428°F) 0.2 oz Tube >60 months

Test Results

i cot neounto		
Test J-STD-004 or other requirements as stated	Test Requirement	Result
Copper Mirror	IPC-TM-650: 2.3.32	L: No breakthrough
Corrosion	IPC-TM-650: 2.6.15	L: No corrosion
Quantitative Halides	IPC-TM-650: 2.3.28.1	L: <0.05%
Electrochemical Migration	IPC-TM-650: 2.6.14.1	L: <1 decade drop (No-clean)
Surface Insulation Resistance 85°C, 85% RH @ 168 Hours	IPC-TM-650: 2.6.3.7	L: ≥100MΩ (No-clean)
Visual	IPC-TM-650: 3.4.2.5	Clear and free from precipitation
Conflict Minerals Compliance	Electronic Industry Citizenship Coalition (EICC)	Compliant
REACH Compliance	Articles 33 and 67 of Regulation (EC) No 1907/2006	Contains no substance >0.1% w/w that is listed as a SVHC or restricted for use in solder materials

Conforms to the following Industry Standards:	
J-STD-004B, Amendment 1 (Solder Fluxes):	Yes
J-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders):	
RoHS 3 Directive (EU) 2015/863:	Yes