


C1206X682F1GACAUTO

SMD Auto COG Flex, Ceramic, 6800 pF, 1%, 100 VDC, COG, SMD, MLCC, FT-CAP, Ultra-Stable, Automotive Grade, 1206



Click here for the 3D model.

| Dimensions | |
|------------|------------------|
| Chip Size | 1206 |
| L | 3.3mm +/-0.4mm |
| W | 1.6mm +/-0.35mm |
| Т | 0.78mm +/-0.20mm |
| В | 0.6mm +/-0.25mm |

| Packaging Specifications | | |
|--------------------------|--------------------------|--|
| Packaging | T&R, 180mm, Plastic Tape | |
| Packaging Quantity | 4000 | |

| General Information | |
|---------------------|--------------------------------------------------------------------|
| Series | SMD Auto COG Flex |
| Style | SMD Chip |
| Description | ${\sf SMD, MLCC, FT-CAP, Ultra-Stable, Automotive} \\ {\sf Grade}$ |
| Features | FT-CAP, Ultra-Stable, Automotive Grade |
| RoHS | Yes |
| Termination | Flexible Termination |
| Marking | No |
| Qualifications | AEC-Q200 |
| AEC-Q200 | Yes |
| Component Weight | 15 mg |
| Shelf Life | 78 Weeks |
| MSL | 1 |

| Specifications | |
|--------------------------------------------------------------------|---------------------------|
| Capacitance | 6800 pF |
| Measurement Condition | 1 kHz 1.0Vrms |
| Capacitance Tolerance | 1% |
| Voltage DC | 100 VDC |
| Dielectric Withstanding Voltage | 250 VDC |
| Temperature Range | -55/+125°C |
| Temperature Coefficient | COG |
| Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC) | 30 ppm/C, 1kHz 1.0Vrms |
| Dissipation Factor | 0.1% 1 kHz 1.0Vrms |
| Aging Rate | 0% Loss/Decade Hour |
| Insulation Resistance | 100 GOhms |

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.